

SOLUTION MX5

Introduction: Solution MX5 contains 5% paraffin wax (mp:52/54 °C). Diluted in styrene.

Applications: A wax solution added to laminating resins if we build laminate wet to wet to 1% max 2% reducing styrene emission. Top (last) layer can contains 2-3% and gelcoats (especially preparing topcoats) at the rate of 2-3% where a completely tack free surface is required.

Typical properties:

Appearance:	Clear, colourless, bit free solution
Odour:	Styrene
Relative density:	1.10 ó 1.20g/ml at 25°C
Flash point:	32°C (closed cup)

Storage: Solution MX5 should be stored in the dark in suitable closed containers. It recommended that the storage temperature should be less than 25°C where practical, but should not exceed 30°C.

Available pack size: 4,5 kg and 20 kg in PEHD container.

Scott Bader d.o.o.

CROATIA, 10000 ZAGREB, Radnička cesta 173i

tel.: +385 1 2406-440

fax: +385 1 2404-573; +385 1 2404-926

e-mail: info@scottbader.hr

