

DISTITRON® 5119 DSX21ZQ

First Emission: 22/06/2012

Version: 04, 02/01/2017

Product type

Unsaturated polyester resin in styrene, Orthophthalic

Appearance

Bluish - Dark - Opalescent

Main resin characteristics

Low styrene emission, Low exothermic peak, With catalyst indicator,
Medium reactivity, Preaccelerated, Thixotropic

Main applications

Reinforced plastics, general purpose

Moulding informations

Hand lay up and Spray up

Shelf life and storage

Store in the shade, out of direct sunlight. Keep storage temperature below 25°C. Unseal container just before use. Shelf-life will be reduced reaching higher temperature.

Precaution for handling

Stir the resin before use, without use air bubbles,
As the resin includes a film-forming agent, we recommend that the laminate should first rubbed down before bonding or relaminating.,
Read carefully the Safety Data Sheet

Note

FEATURES OF THE LIQUID RESIN

Properties	Test Method	Unit	Typical values
Specific weight at 20°C		g/cm ³	1,10
Brookfield viscosity at 25°C, sp 2 rpm 20	MT-CUT25V	mPa.s	600 - 780
Solid content	MT-CU001C	%	57 - 61
Reactivity	at 25°C + 1,5% MEKP50		
Gel time	RS.08.G	minutes	20 - 27
Delta	RS.08.G	minutes	9 - 16
Exothermic peak	RS.08.G	°C	120 - 145
Shelf life at 23°C in the dark	MT-CU002S	months	3

PROPERTIES OF THE CURED UNREINFORCED RESIN

Curing cycle	24h at 23°C + 2h at 100°C + 1h at 100°C		
Tensile strength	ISO 527 (2012)	MPa	50
Tensile modulus	ISO 527 (2012)	MPa	3900
Elongation at break	ISO 527 (2012)	%	1,5
Flexural strength	ISO 178/B (2010)	MPa	85
Flexural modulus	ISO 178/B (2010)	MPa	3900
HDT	ISO 75 -2A (2013)	°C	65
Glass transition	ASTM E 1545 (2011)	°C	78
Barcol hardness at 25°C	ASTM D 2583 (2007)	units	42

The information contained in this document (which is to be intended only for explanatory purposes) is correct and accurate and is based on our technical and scientific knowledge and on literature at the date of publication. Such information relates only to use of the products in the pure state and for the purposes stated herein. Nothing in the information contained in this document shall be deemed to be a warranty or a representation (explicit or implicit) by the manufacturer, and/or taken or construed as infringing of any existing patents. The manufacturer shall not be under any liability or responsibility for any of the information provided under this document or for any errors, omissions or misstatements, even with regard to results to be obtained through the use of the aforesaid information.