

E-glass fabric EE 23 P

Mass per unit area (g/m²)	23 ±5%	ISO 4605
Weave	plain	ISO 2113
Standard width (mm)	1030 ±2,5%	
Laminate thickness (mm)	0,032 ±2,5%	(**)
Other information	Loomstate	

(**) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Nominal construction		WARP		WEFT	
Fibre description		E glass EC 5 - 5,5 tex		E glass EC 5 - 5,5 tex	
Thread Count	ends/cm.	26.0	ISO 4602	15.5	ISO 4602
Weight distribution	gr/sqm.	E glass fibre:		E glass fibre:	
	%	%		22 %	

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risks and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.