

E-glass fabric UNIGLASS 48 P

<b>Mass per unit area (g/m<sup>2</sup>)</b>	48 ±5%	ISO 4605
<b>Weave</b>	plain	ISO 2113
<b>Standard width (mm)</b>	1270 ±2,5%	
<b>Laminate thickness (mm)</b>	0,047 ±2,5%	(**)
<b>Other information</b>	Loomstate	

(\*\*) Theoretical thickness for an epoxy laminate with 40% of reinforcement in volume.

Nominal construction		WARP		WEFT	
Fibre description		E glass EC 5 - 11 tex		E glass EC 5 - 12 tex	
Thread Count	ends/cm.	24.0	ISO 4602	18.2	ISO 4602
Weight distribution	gr/sqm.	E glass fibre: 26		E glass fibre: 22	
	%	54 %		46 %	

Note: Technical information furnished is based on laboratory findings and believed to be correct. No warranties of any kind are made except that the materials supplied are of standard quality. All risks and liabilities arising from handling, storage and use of products, as well as compliance with applicable legal restrictions, rests with the user.