

## Product - Data Sheet

### Lightweight Silica Filler

### Stiff 305/0

Item: R543050000000 - Stiff 305/0 Bags with 14.5 kg

#### General Technical Information

Specific Gravity in g/cm <sup>3</sup>	0,30
Resistance to Light	good
Weather Resistance	good
Resistance to Ageing	good
Acid Resistance	good
Alkali Resistance	moderate
Solvent Resistance	good

#### Physical Properties

Colour	white
Shape in Section	hollow spheres
Melting Temperature in °C approx.	1.200
Wet Content on Delivery in % max.	1
Bulk Density in g/l approx.	145
Durability from Delivery Date	12 months
Air Jet Sieve ISO 4610 in % - 160 µm	< 21
Air Jet Sieve ISO 4610 in % - 315 µm	-

## Disclaimer

May contain traces of foreign particles. The stated fibre length corresponds to an average value and is based on a Gaussian length distribution.

We warrant that the product complies with the data and properties specified in this data sheet. Beyond that, we do not guarantee any further properties and/or a specific application, unless we agree in writing on an extended specification which indicates otherwise.

The values listed under the General Technical Information refer to literature data and information from our suppliers. We do not assume any warranty for these.

The information provided in our Technical Data Sheets, as well as our technical advice, in particular with regard to the intended use, are given to the best of our knowledge, but are to be regarded only as non-binding information, also with regard to any industrial property rights of third parties.

The consultation does not release you from your own examination of the information provided by us. Information, in particular in our safety information, on the technical data sheets, as well as the suitability for the intended processes and purposes must be checked and verified by you. The application, use and processing of our products, as well as the products manufactured by you on the basis of our technical application advice, are beyond our control and are therefore exclusively your own responsibility. The sale of our products and our advice are based on our General Terms and Conditions of Sale and Delivery as amended from time to time.

## Storage Information

Store unopened at +5°C to +30°C as well as protected from moisture, drafts and UV-radiation.